



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

An ISO 9001:2008 Registered Company
An ISO 14001: 2004 Registered Company

GOVT.RECOGNISED EXPORT HOUSE

TECHNICAL SPECIFICATIONS

QUALITY : NATURAL RUBBER SHEET CODE: ZEN STAR ECO

PROPERTIES	TEST METHOD	VALUES	
		FPS UNITS	METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.30 ± 0.05	1.30 ± 0.05
HARDNESS	DIN 53505	65 ± 5 Sh A	65 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	853 PSI	60 kg/cm ²
ELONGATION AT BREAK (min)	DIN 53504	350%	350%
ABRASION RESISTANCE (max)	DIN 53515	200 mm ³	200 mm ³
COMPRESSION SET (70°C/24 hrs/25% set) (max)	DIN 53508	50%	50%
TEAR RESISTANCE (Angular) min	DIN 53505	140 Lbs/Inch	25 Kg/cm
CHANGE IN PROPERTIES			
HEAT AGEING (72 hrs. AT 70°C)			ASTM D573
--- HARDNESS (Pts)		+ 5 (Max)	+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / -25	+ 10 / -25
--- ELONGATION AT BREAK (%)		+ 10 / -25	+ 10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS/IN			ASTM D 471
IRM OIL NO.1		NOT RECOMMENDED	NOT RECOMMENDED
IRM OIL NO.2		NOT RECOMMENDED	NOT RECOMMENDED
IRM OIL NO.3		NOT RECOMMENDED	NOT RECOMMENDED
CHEMICAL RESISTANCE			
--- OZONE		FAIR	ASTM D 1149 FAIR
--- DILUTE ACIDS AND BASES		GOOD	GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED	NOT RECOMMENDED
--- OILS		NOT RECOMMENDED	NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED	NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 75 °C	-40° to + 75 °C
COLOUR		BLACK	BLACK



141/144,14TH FLOOR, FREE PRESS HOUSE, FREE PRESS JOURNAL MARG
215,NARIMAN POINT MUMBAI - 400021

Email: info@zenithrubber.com

Website: www.zenithrubber.com