



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

An ISO 9001:2008 Registered Company
An ISO 14001:2004 Registered Company

GOVT.RECOGNISED EXPORT HOUSE

TECHNICAL SPECIFICATIONS

QUALITY : COMMERCIAL SBR RUBBER
CODE : SX 50150

| PROPERTIES | TEST METHOD | VALUES | TEST METHOD | VALUES |
|---------------------------------------|-------------|-----------------|-------------|-----------------------|
| | | FPS UNITS | | METRIC UNITS |
| SPECIFIC GRAVITY | ASTM D297 | 1.5 | DIN 53508 | 1.5 |
| HARDNESS | ASTM D2240 | 50 ± 5 Sh A | DIN 53505 | 50 ± 5 Sh A |
| TENSILE STRENGTH (min) | ASTM D412 | 426 PSI | DIN 53504 | 30 kg/cm ² |
| ELONGATION AT BREAK (min) | ASTM D412 | 200% | DIN 53504 | 200% |
| TEAR RESISTANCE (Angular) min | ASTM D624 | 90 Lbs/Inch | DIN 53515 | 16 Kg/cm |
| CHANGE IN PROPERTIES | | | | |
| HEAT AGEING (72 hrs. AT 70 °C) | ASTM D573 | | | |
| --- HARDNESS (Pts) | | + 5 (Max) | | + 5 (Max) |
| --- TENSILE STRENGTH (%) | | + 10 / -25 | | + 10 / -25 |
| --- ELONGATION AT BREAK (%) | | + 10 / -25 | | + 10 / -25 |
| VOLUME SWELL : AT 70° C FOR 72 HRS/IN | ASTM D 471 | | | |
| ASTM OIL NO.1 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| ASTM OIL NO.2 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| ASTM OIL NO.3 | | NOT RECOMMENDED | | NOT RECOMMENDED |
| CHEMICAL RESISTANCE | | | | |
| --- OZONE | ASTM D 1149 | NOT RECOMMENDED | | NOT RECOMMENDED |
| --- DILUTE ACIDS AND BASES | | NOT RECOMMENDED | | NOT RECOMMENDED |
| --- CONCENTRATED ACIDS AND BASES | | NOT RECOMMENDED | | NOT RECOMMENDED |
| --- OILS | | NOT RECOMMENDED | | NOT RECOMMENDED |
| --- SOLVENTS | | NOT RECOMMENDED | | NOT RECOMMENDED |
| TEMPERATURE RANGE | | -30° to + 70° C | | -30° to + 70° C |
| COLOUR | | BLACK | | BLACK |



141/144,14TH FLOOR, FREE PRESS HOUSE, FREE PRESS JOURNAL MARG 215,NARIMAN POINT
MUMBAI - 400021

Email: info@zenithrubber.com

Website: www.zenithrubber.com