



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

An ISO 9001:2008 Registered Company
An ISO 14001: 2004 Registered Company

GOVT.RECOGNISED EXPORT HOUSE

TECHNICAL SPECIFICATIONS

QUALITY : COMMERCIAL NITRILE RUBBER CODE: NB 5010

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUE
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.45 ± 0.05	ASTM D297	1.45 ± 0.05
HARDNESS	DIN 53505	50 ± 5 Sh A	ASTM D2240	50 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	569 PSI	ASTM D412	40 kg/cm ²
ELONGATION AT BREAK (min)	DIN 53504	200%	ASTM D412	200%
COMPRESSION SET (70 °C/24 hrs/25% set) (max)	DIN ISO 815-1	40%	ASTM D395 METHOD B	40%
TEAR RESISTANCE (Angular) min	DIN 53515	100 Lbs/Inch	ASTM D624	18 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70 °C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / - 25		+ 10 / - 25
--- ELONGATION AT BREAK (%)		+ 10 / - 25		+ 10 / - 25
VOLUME SWELL : AT 70° C FOR 72 HRS/IN			ASTM D 471	
IRM OIL NO.1		+ 30%		+ 30%
IRM OIL NO.2		+ 44%		+ 44%
IRM OIL NO.3		+ 85%		+ 85%
POLYMER CONTENT (NITRILE)		10%		10%
CHEMICAL RESISTANCE				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		FAIR		FAIR
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30 ° to +90° C		-30 ° to +90° C
COLOUR		BLACK		BLACK



141/144,14TH FLOOR, FREE PRESS HOUSE, FREE PRESS JOURNAL MARG 215,NARIMAN POINT MUMBAI – 400021

Email: info@zenithrubber.com

Website: www.zenithrubber.com