



GREYFINE NR

grey | density 1.05 | hardness 40

03/07/2014

MEDIUM WEAR SHEETING: FINE GRAIN SIZE MATERIAL

FEATURES

Wear resistant natural rubber, grey.

ADVANTAGES

- ▶ Excellent mechanical properties: tensile strength, elongation at break, tear resistance, abrasion, etc.
- ▶ Excellent resistance to fine grain size products projection and fretting wear: sand, shot blasting, fine particles, abrasive dust, etc.
- ▶ Corrosion protection
- ▶ Noise and vibration propagation reduction
- ▶ Possibility to be produced with bonding layer for cold vulcanizing or with steel backing for mechanical fixing

BENEFITS

- ▶ Performance
- ▶ Safety
- ▶ Reliability
- ▶ Service life

APPLICATIONS

Hoppers, chutes, operating cyclones, vibrating lines, silos, etc., linings to protect equipment against very abrasive fine grain size products wear, due to their very nature (rock, wood, metal, all fine particle size materials, chemical products, etc.), density and hardness (medium to high), forms (fine particles, bulks, etc.), with dry conditions and maximum temperature + 70 °C.

Manufacturing of rubber skirts.

Hanging panels fostering materials cleaning and removal.

Areas of activity: sand and gravel quarries, aggregate and cement industries, concrete plants, etc.

www.trelleborg.com/elastomerlaminates

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

	Measured characteristics	Standard	Value	
MECHANICAL				
	<i>Rubber compound</i>		NR R488	
	<i>Density</i>		1.05 ± 0.05	g/cm ³
	<i>Hardness</i>	ASTM D2240	40 ± 5	Shore A
	<i>Tensile strength</i>	ISO 37	≥ 16	MPa
	<i>Elongation at break</i>	ISO 37	≥ 600	%
	<i>Abrasion resistance (5 N)</i>	ISO 4649	≤ 100	mm ³
	<i>Compression set after 22 h at 70 °C</i>	ISO 815-1	≤ 35	%
TEMPERATURE				
	<i>Working temperature</i>		- 40/+ 70	°C
AGEING				
	<i>Δ Hardness after 70 h at 70 °C</i>	ASTM D573	≤ -3	Shore A
	<i>Δ Tensile strenght after 70 h at 70 °C</i>	ASTM D573	≤ -15	%
	<i>Δ Elongation at break after 70 h at 70 °C</i>	ASTM D573	≤ -20	%
CHEMICAL RESISTANCE				
	<i>Diluted acids and bases</i>	<i>Concentrated acids and bases</i>	<i>Ozone</i>	<i>Oils and hydrocarbons</i>
	Very good	Good	Medium	Non suitable

DIMENSIONS

Thickness (mm)		Width (mm)		Length (m)		Weight (kg/m ²)	Pattern
3	± 0.3	1400	± 2 %	10	± 2 %	3.15	2 smooth sides
4	± 0.4	1400	± 2 %	10	± 2 %	4.20	2 smooth sides
5	± 0.4	1400	± 2 %	10	± 2 %	5.25	2 smooth sides
6	± 0.5	1400	± 2 %	10	± 2 %	6.30	2 smooth sides
8	± 0.7	1400	± 2 %	10	± 2 %	8.40	2 smooth sides
10	± 1.0	1400	± 2 %	10	± 2 %	10.50	2 smooth sides
12	± 1.0	1400	± 2 %	5	± 2 %	12.60	2 smooth sides
15	± 1.0	1400	± 2 %	5	± 2 %	15.75	2 smooth sides

IDENTIFICATION

<i>Branding</i>	Without.
<i>Packaging</i>	Thickness ≤ 6 mm rolled on cardboard tube Ø 80 mm. Thickness > 6 mm in roll.
<i>Wrapping</i>	Black polyethylene film.
<i>Labelling</i>	Self-adhesive label indicating product name, dimensions, area in m ² , nominal weight, and product code to allow product traceability.