



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

An ISO 9001:2008 Certified Company
An ISO 14001:2004 Certified Company

GOVT.RECOGNISED EXPORT HOUSE

TECHNICAL SPECIFICATIONS

QUALITY : NATURAL RUBBER BLACK (ABRASION RESISTANT SHEET) CODE: AB 60117

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.17±0.05	ASTM D297	1.17±0.05
HARDNESS	DIN 53505	60 ± 5 Sh A	ASTM D2240	60 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	1638 PSI	ASTM D412	115 kg/cm2
ELONGATION AT BREAK (min)	DIN 53504	450%	ASTM D412	450%
ABRASION RESISTANCE (max)	DIN 53516	120 mm3	ASTM D5963	120 mm3
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	30%	ASTM D395 METHOD B	30%
TEAR RESISTANCE (Angular) min	DIN 53515	168 Lbs/Inch	ASTM D624	30 Kg/cm
CHANGE IN PROPERTIES AFTER HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / - 25		+ 10 / - 25
--- ELONGATION AT BREAK (%)		+ 10 / - 25		+ 10 / - 25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70°C		-30° to + 70°C
COLOUR		BLACK		BLACK



141/144,14TH FLOOR, FREE PRESS HOUSE, FREE PRESS JOURNAL MARG 215,NARIMAN POINT MUMBAI – 400021

Email: info@zenithrubber.com Website: www.zenithrubber.com