



# ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

An ISO 9001:2008 Registered Company  
An ISO 14001: 2004 Registered Company

GOVT.RECOGNISED EXPORT HOUSE

## TECHNICAL SPECIFICATIONS

### QUALITY : SILICONE RUBBER SHEET CODE: SI 60120 FG

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	ASTM D297	1.20	DIN 53508	1.20
HARDNESS	ASTM D2240	60 ± 5 Sh A	DIN 53505	60 ± 5 Sh A
TENSILE STRENGTH ( min )	ASTM D412	858 PSI	DIN 53504	60 kg/cm2
ELONGATION AT BREAK ( min )	ASTM D412	200%	DIN 53504	200%
COMPRESSION SET (70° C/24 hrs/25% set) (max)	ASTM D395 METHOD B	40%	DIN 53517	40%
TEAR RESISTANCE ( Angular ) min	ASTM D624	112 Lbs/Inch	DIN 53515	20 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING ( 72 hrs. AT 100 °C )	ASTM D573			
--- HARDNESS (Pts)		+ 3 (Max)		+ 3 (Max)
--- TENSILE STRENGTH (%)		+ 5 / - 5		+ 5 / - 5
--- ELONGATION AT BREAK (%)		+ 5 / - 5		+ 5 / - 5
VOLUME SWELL : AT 70° C FOR 72 HRS/IN	ASTM D 471			
ASTM OIL NO.1		+ 5%		+ 5%
ASTM OIL NO.2		+ 7%		+ 7%
ASTM OIL NO.3		+ 25%		+ 25%
<b>CHEMICAL RESISTANCE</b>				
--- OZONE	ASTM D 1149	EXCELLENT		EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
--- OILS		GOOD		GOOD
--- SOLVENTS		FAIR		FAIR
TEMPERATURE RANGE		-90 ° to + 230° C		-90 ° to + 230° C
COLOUR		WHITE		



141/144,14<sup>TH</sup> FLOOR, FREE PRESS HOUSE, FREE PRESS JOURNAL MARG 215,NARIMAN POINT MUMBAI - 400021

Email: [info@zenithrubber.com](mailto:info@zenithrubber.com)

Website: [www.zenithrubber.com](http://www.zenithrubber.com)